

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 08-225443

(43)Date of publication of application : 03.09.1996

---

(51)Int.Cl.

A61K 9/70  
A61K 9/70  
C08F 8/44  
C08L 33/02

---

(21)Application number : 07-327104

(71)Applicant : TAISHO PHARMACEUT CO LTD

(22)Date of filing : 15.12.1995

(72)Inventor : YAMAZAKI KAZUO  
ISHIKAWA JUNKO  
NARA MASATO  
KOMATA KAZUOKI

---

(30)Priority

Priority number : 06314811    Priority date : 19.12.1994    Priority country : JP

---

(54) PLASTER FOR POULTICE

(57)Abstract:

PURPOSE: To obtain a plaster for poultice causing no swelling out or backside oozing thereof from the relevant preparations during its storage and/or distribution after spreading plaster, and capable of well-retaining its tackiness for a long period, by blending specific crosslinking agents in a highly hydrous base containing an acrylic compound.

CONSTITUTION: This plaster is obtained by blending a base composed of an acrylic compound (e.g. polyacrylic acid) and  $\geq 70$ wt.% of water with pref. 0.02-0.1wt.%, based on the whole plaster, of crosslinking agents, i.e., (A) aluminum magnesium hydroxide or aluminum glycinate and (B) aluminum hydroxide at the weight ratio A/B of (1:20) to (7:1). It is preferable that the amount of the acrylic compound to be blended be 8-15wt.% of the whole plaster. Besides, it is recommended that this plaster be adjusted to pH 4-6 in order to smoothly advance the crosslinking of the base.

---

LEGAL STATUS

[Date of request for examination]

18.07.2002